

(19)



JAPANESE PATENT OFFICE

PATENT ABSTRACTS OF JAPAN

(11) Publication number: **11315185 A**

(43) Date of publication of application: **16.11.99**

(51) Int. Cl

C08L 51/06
C08F 8/20
C08F255/00
C09D151/06

(21) Application number: **11008886**

(22) Date of filing: **18.01.99**

(30) Priority: **21.01.98 JP 10 9328**

(71) Applicant: **NIPPON PAPER INDUSTRIES CO LTD**

(72) Inventor: **UEDA TAKAAKI**
URATA KEIJI

(54) BINDER RESIN COMPOSITION AND ITS PRODUCTION

(57) Abstract:

PROBLEM TO BE SOLVED: To obtain a new binder resin composition used in cases for coating polyolefinic moldings.

SOLUTION: This binder resin composition comprises a carboxyl group- obtaining chlorinated syndiotactic polyolefin resin having a chlorine content of 10-40 wt.%, the grafting amount of an α,β -unsaturated

carboxylic acid and/or its acid anhydride in the range of 1-10 wt.%, and a weight-average mol.wt. of 30,000-220,000, an organic solvent, and preferably further an epoxy compound as a stabilizer. The carboxyl group-containing chlorinated syndiotactic polyolefin resin obtained from a polyolefin resin produced from a metallocene compound has a good liquid property in spite of a low chlorine content, and further has excellent adhesivity and solvent resistance to polyolefinic raw materials.

COPYRIGHT: (C)1999,JPO